



SMD Comm X8G HT150C, Ceramic, 1,500 pF, 10%, 200 VDC, X8G, SMD, MLCC, High Temperature, Ultra-Stable, 0603, 0.5 mm



General Information		
Series	SMD Comm X8G HT150C	
Style	SMD Chip	
Description	SMD, MLCC, High Temperature, Ultra-Stable	
Features	High Temperature, Ultra-Stable	
RoHS	Yes	
Termination	Tin	
Marking	No	
AEC-Q200	No	
Typical Component Weight	4.6 mg	
Shelf Life	78 Weeks	
MSL	1	

Dimensions	
Chip Size	0603
L	1.6mm +/-0.15mm
W	0.8mm +/-0.15mm
Т	0.85mm +/-0.07mm
S	0.5mm MIN
В	0.35mm +/-0.15mm

L	1.011111 +/ -0.1511111
W	0.8mm +/-0.15mm
Т	0.85mm +/-0.07mm
S	0.5mm MIN
В	0.35mm +/-0.15mm
Packaging Specifications	

W	0.8mm +/-0.15mm	Tolerance	10%
Т	0.85mm +/-0.07mm	Voltage DC	200 VDC
S	0.5mm MIN	Dielectric Withstanding Voltage	500 VDC
В	0.35mm +/-0.15mm	Temperature Range	-55/+150°C
		Temp. Coefficient	X8G
ackaging Specifications		Capacitance Change with	30 ppm/C, 1kHz 1.0Vrms
Packaging	T&R, 330mm, Paper Tape	Reference to +25°C and 0 VDC Applied (TCC)	
Packaging Quantity 10000	Dissipation Factor	0.1% 1 kHz 1.0Vrms	
		Aging Rate	0% Loss/Decade Hour: Referee Time is 1000 Hours

**Specifications** 

Capacitance

Measurement Condition	1 kHz 1.0Vrms	
Tolerance	10%	
Voltage DC	200 VDC	
Dielectric Withstanding Voltage	500 VDC	
Temperature Range	-55/+150°C	
Temp. Coefficient	X8G	
Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC)	30 ppm/C, 1kHz 1.0Vrms	
Dissipation Factor	0.1% 1 kHz 1.0Vrms	
Aging Rate	0% Loss/Decade Hour: Referee Time is 1000 Hours	
Insulation Resistance	100 GOhms	

1,500 pF

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

Generated 05/10/2025 © 2006 - 2025 YAGEO