

C0603X339D2TACAUTO

SMD Auto X8G HT150C Flex, Ceramic, 3.3 pF, +/-0.5 pF, 200 VDC, X8G, SMD, MLCC, High Temperature, Ultra-Stable, Automotive Grade, 0603,



General Information	
Series	SMD Auto X8G HT150C Flex
Style	SMD Chip
Description	SMD, MLCC, High Temperature, Ultra-Stable, Automotive Grade
Features	High Temperature, Ultra-Stable, Automotive Grade
RoHS	Yes
Termination	Flexible Termination
Marking	No
Qualifications	AEC-Q200
AEC-Q200	Yes
Typical Component Weight	4.6 mg
Shelf Life	78 Weeks
MSL	1

Dimensions	
Chip Size	0603
L	1.6mm +/-0.17mm
W	0.8mm +/-0.15mm
Т	0.8mm +/-0.15mm
S	0.4mm MIN
В	0.45mm +/-0.15mm

Chip Size	0603	Capacitance	3.3 pF
L	1.6mm +/-0.17mm	Measurement Condition	1 MHz 1.0Vrms
W	0.8mm +/-0.15mm	Tolerance	+/-0.5 pF
Т	0.8mm +/-0.15mm	Voltage DC	200 VDC
S	0.4mm MIN	Dielectric Withstanding Voltage	500 VDC
В	0.45mm +/-0.15mm	Temperature Range	-55/+150°C
		Temp. Coefficient	X8G
Packaging Specifications		Capacitance Change with	30 ppm/C, 1MegaHz 1.0
Packaging	T&R, 180mm, Paper Tape	Reference to +25°C and 0 VDC Applied (TCC)	
Packaging Quantity	4000	Dissipation Factor	0.1% 1 MHz 1 0Vrms

Specifications

n +/-0.17mm	Measurement Condition	11411 101/
•	Medsarement condition	1 MHz 1.0Vrms
m +/-0.15mm	Tolerance	+/-0.5 pF
m +/-0.15mm	Voltage DC	200 VDC
m MIN	Dielectric Withstanding Voltage	500 VDC
nm +/-0.15mm	Temperature Range	-55/+150°C
	Temp. Coefficient	X8G
180mm, Paper Tape	Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC)	30 ppm/C, 1MegaHz 1.0Vrms
	Dissipation Factor	0.1% 1 MHz 1.0Vrms
	Aging Rate	0% Loss/Decade Hour: Referee Time is 1000 Hours
	Insulation Resistance	100 GOhms

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

Generated 05/03/2025 © 2006 - 2025 YAGEO