



SMD Comm X8G HT150C Flex, Ceramic, 1,500 pF, 20%, 200 VDC, X8G, SMD, MLCC, High Temperature, Ultra-Stable, 1210, 1.5 mm



General Information		
Series	SMD Comm X8G HT150C Flex	
Style	SMD Chip	
Description	SMD, MLCC, High Temperature, Ultra-Stable	
Features	High Temperature, Ultra-Stable	
RoHS	Yes	
Termination	Flexible Termination	
Marking	No	
AEC-Q200	No	
Typical Component Weight	40 mg	
Shelf Life	78 Weeks	
MSL	1	

1,500 pF

1 kHz 1.0Vrms

100 GOhms

Dimensions	
Chip Size	1210
L	3.3mm +/-0.4mm
W	2.6mm +/-0.3mm
Т	1mm +/-0.10mm
S	1.5mm MIN
В	0.6mm +/-0.25mm
R	0.6mm +/-0.25mm

W	2.6mm +/-0.3mm
Т	1mm +/-0.10mm
S	1.5mm MIN
В	0.6mm +/-0.25mm
Packaging Specifications	

2.6mm +/-0.3mm	Tolerance	20%
1mm +/-0.10mm	Voltage DC	200 VDC
1.5mm MIN	Dielectric Withstanding Voltage	500 VDC
0.6mm +/-0.25mm	Temperature Range	-55/+150°C
	Temp. Coefficient	X8G
Packaging Specifications		30 ppm/C, 1kHz 1.0Vrms
T&R, 330mm, Plastic Tape	Reference to +25°C and 0 VDC Applied (TCC)	
Packaging Quantity 10000	Dissipation Factor	0.1% 1 kHz 1.0Vrms
	Aging Rate	0% Loss/Decade Hour: Referee Time is 1000 Hours
	1mm +/-0.10mm 1.5mm MIN 0.6mm +/-0.25mm T&R, 330mm, Plastic Tape	1.5mm MIN Dielectric Withstanding Voltage 0.6mm +/-0.25mm Temperature Range Temp. Coefficient Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC) Dissipation Factor

Specifications

Measurement Condition

Insulation Resistance

Capacitance

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

Generated 05/05/2025 © 2006 - 2025 YAGEO