


C2220C273K2TACTU

Aliases (C2220C273K2TAC7800)

SMD Comm X8G HT150C, Ceramic, 0.027 uF, 10%, 200 VDC, X8G, SMD, MLCC, High Temperature, Ultra-Stable, 2220, 3.5 mm



General Information		
Series	SMD Comm X8G HT150C	
Style	SMD Chip	
Description	SMD, MLCC, High Temperature, Ultra-Stable	
Features	High Temperature, Ultra-Stable	
RoHS	Yes	
Termination	Tin	
Marking	No	
AEC-Q200	No	
Typical Component Weight	130 mg	
Shelf Life	78 Weeks	
MSL	1	

Dimensions	
Chip Size	2220
L	5.7mm +/-0.4mm
W	5mm +/-0.4mm
Т	1mm +/-0.15mm
S	3.5mm MIN
В	0.6mm +/-0.35mm

_	S.711111 / S. 111111
W	5mm +/-0.4mm
Т	1mm +/-0.15mm
S	3.5mm MIN
В	0.6mm +/-0.35mm
Packaging Specifications	

W	5mm +/-0.4mm	Tolerance	10%
	,		
Т	1mm +/-0.15mm	Voltage DC	200 VDC
S	3.5mm MIN	Dielectric Withstanding Voltage	500 VDC
В	0.6mm +/-0.35mm	Temperature Range	-55/+150°C
		Temp. Coefficient	X8G
Packaging Specifications		Capacitance Change with	30 ppm/C, 1kHz 1.0Vrms
Packaging	T&R, 180mm, Plastic Tape	Reference to +25°C and 0 VDC Applied (TCC)	
Packaging Quantity	1000	Dissipation Factor	0.1% 1 kHz 1.0Vrms
		Dissipation ractor	0.170 T KI 12 1.0 VIII.13
		Aging Rate	0% Loss/Decade Hour: Referee Time is 1000 Hours

Specifications

Capacitance

Measurement Condition	1 kHz 1.0Vrms
Tolerance	10%
Voltage DC	200 VDC
Dielectric Withstanding Voltage	500 VDC
Temperature Range	-55/+150°C
Temp. Coefficient	X8G
Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC)	30 ppm/C, 1kHz 1.0Vrms
Dissipation Factor	0.1% 1 kHz 1.0Vrms
Aging Rate	0% Loss/Decade Hour: Referee Time is 1000 Hours
Insulation Resistance	37.037 GOhms

0.027 uF

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

Generated 05/05/2025 © 2006 - 2025 YAGEO